



Product Data

Chameleon™ Liquid Black A875

3700 E. Olympic Blvd. • Los Angeles • CA • 90023 • T: 323-269-7311 • F: 323-269-1053
7101 E. Muirkirk Road • Beltsville • MD • 20705 • T: 301-210-3400 • F: 301-210-4967
www.daviscolors.com • info@daviscolors.com

Pigment Black 11 • Color Index No. 77499 • CAS 1317-65-9

Chameleon™ Liquid Black Iron Oxide A875

Description

Chameleon™ Liquid Black A875 is a high tinting-strength suspension of Synthetic Iron Oxide Black pigment in water with surfactants and stabilizers that is designed specifically for use in a Chameleon™ automatic color dosing system. Black Iron Oxide is a pigment of extremely fine particle size, high tint strength and color stability and durability. Chameleon™ Liquid Black A875 is made by grinding Black iron oxide in water on high-speed grinding equipment for several hours in batch sizes of 600 gallons. Stabilizers and biocides are added to increase shelf life and keep the iron oxide in suspension. If settled, it may be re-suspended by simply stirring or recirculating the liquid. Each batch is measured throughout the process and verified on spectrophotometer equipment to certify it is on standard for tint strength and shade. It meets or exceeds ASTM C979-82 standards for pigments used in cement and is color-stable in processing temperatures below 180°C (365°F). Iron oxide is stable under exposure to sunlight and UV radiation, and is alkali and weather resistant. Chameleon™ Liquid Black A875 is packaged in 4000 Lb. semi-bulk disposable bins and also available in bulk tanker deliveries. *Uses: Chameleon™ automatic dosing system for Ready Mix, precast and other concrete products.*

Composition/Typical Properties

Fe ₂ O ₃ content (%)	57 – 61
SiO ₂ content (%)	<1
H ₂ O content (%)	39 – 43
Weight per Gallon (lbs)	15.0
Specific Gravity (g/cm ³)	1.83
Dry Solids (lbs/gal)	9.0
Water Soluble Salts (%)	<0.5
Viscosity (KU)	88
Viscosity (CPS)	1120
pH	8.5
Surfactant type	Anionic
Biocide type	Non-Mercurial
Settling	Very Slight
Particle Shape	Spherical
Predominant Particle Size (µm)	0.2 – 0.4

Typical Trace Metal Content in Parts Per Million (ppm)

Arsenic (As)	<1
Barium (Ba)	<10
Cadmium (Cd)	<0.1
Chromium (III) (Cr)	<0.2
Lead (Pb)	<1
Mercury (Hg)	<0.01
Selenium (Se)	<1
Silver (Ag)	<0.1

The values for typical contents and trace metals are provided as general information only. They are approximate values for reference and not specifications utilized in our standard QC procedures for color and consistency.

This product information is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best knowledge of Rockwood Pigments, Inc. or obtained from sources we believe are accurate. We disclaim any legal responsibility for use or reliance on this information and expressly disclaim that use of this product, either alone or in combination with other materials, will not violate the claims of any patent or rightful claim of any third party. Since you are in control of the application, process and conditions of use of our products, you have an obligation to test the products supplied by us to determine their suitability for the intended processes and uses. Despite this, if liability should be established for any damage, buyer's sole remedy shall be refund of product purchase price from point of purchase. We will, of course, provide consistent quality of our products within the scope of our General Conditions of Sale and Delivery. Before using any chemical, read its label and Material Safety Data Sheet.

November 10, 2003